

Konudur Flexfit CS

Reaction resin based filler for flexible embedding of CIPP-liners to manhole walls



AREAS OF APPLICATION

- Embedding of CIPP-liner (Polyester göass, EP needle felt) to manhole walls)
- Embedding of laterals in manholes and accessible sewage constructions
- Sealing of manhole ring joints (without back-bearing water)
- Sealing of leaking sleeves in accessible sewage constructions (without back-bearing water)
- REACH-assessed exposure scenarios: periodical inhalation, application, long-term water-contact
- Application with MC-Fastpack Powertool

APPLICATION ADVICE

Substrate preparation: The substrate has to be clean and free of any loose particles, dust, oil, grease or any waste water residuals. Plastic based substrates are to be roughened, afterwards cleaned / washed and dried before the filler is applied. When embedding of CIPP-liner, any pre-liner and liner coatings are to be removed mechanically in all areas where the filler is to be applied. Mineral based substrates might be dry or damp. A closed water film is to be avoided. For more information, also concerning application details, have a look on the data sheet "General application advice for the connection of CIPP liners to manholes".

Mixing: Konudur Flexfit CS is made up of two components, component A (base) and component B (hardener). Components A and B are mixed using the static mixer supplied with the cartridge. Only the supplied mixers may be used.

Application (plugging / filling): Using static mixers in combination with a suitable tool (e.g. trowel, spatula) Konudur Flexfit CS is applied to the prepared surface by hand. In order to optimize the adhesive bond on matt damp substrates, lightly aged material can be reworked with pressure (press on). Within the pot life Konudur Flexfit CS can be re-smoothed with vegetable oil. Application details are given in the data sheet "General application advice for the connection of CIPP liners to manholes".

Resistance to water contact: The resistance to water contact / back to service time of Konudur Flexfit CS depends on material, substrate and air temperature. For details on this topic see table "Technical values & product characteristics". Keep damaged spot / application area of Konudur Flexfit free of waste water during application and during curing phase. The first contact to water is possible as soon as the material surface has stiffened (can still be sticky).

Cleaning: Within pot life all equipment might be cleaned using MC-Reinigungsmittel U (thinner). Partially or fully cured material can only be removed by mechanical means.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Mixing ratio	parts by volume	1 : 1	comp. A : comp. B
Density	kg/l	approx. 1.61 approx. 1.5 approx. 1.48	component A component B mixture
Working time	minutes	approx. 7 - 8	at 15° C
Application conditions	°C	≥ 5 ≤ 30 ≥ 15 ≤ 25	air and substrate temperatures material temperature
Viscosity	Pa·s	approx. 200 approx. 220 approx. 540	component A component B mixture
Tensile strength	N/mm ²	≥ 2	EN ISO 527
Shore D hardness		≥ 25	EN ISO 868
Resilient after (chemically)	days	approx. 7	
Resilient after (mechanically)	days	approx. 7	
Water resistant after ¹⁾	minutes	approx. 30	
Ultimate elongation	%	≥ 17	EN ISO 527
Tensile strength	N/mm ²	≥ 2 ≥ 2 ≥ 2 approx. 1 ≥ 2	EN ISO 4624 Concrete (moist) Sewage clinker / stoneware (wet) PVC (moist) PE-HD (moist) GRP / manmade fibre liner

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

1) under sewerage atmosphere

Equipment cleaning agent	MC-Reinigungsmittel U
Colour	anthracite grey
Delivery form	Cartridge 400 ml. 8 cartridges per box + 10 static mixers
Storage	Can be stored in original sealed packages at temperatures between 5°C and 20°C in dry conditions for at least 12 months.
Packaging disposal	Make sure single-use containers are completely empty.

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : PU20

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300020075]