MC-CarboSolid 1209 TX

Thixotropic adhesive for CF-sheets for structural reinforcement



PRODUCT PROPERTIES	 Two-component adhesive based on epoxy resin High mechanical strength Application even at high temperatures (≤ 40 °C) Excellent adhesive between CF-sheets and prepared substrate High structural stability
AREAS OF APPLICATION	 Adhesive for high-tensile reinforcing sheets for reinforcement of components made of reinforced concrete and brickwork REACH-assessed exposure scenarios: periodical water-contact, periodical inhalation, application
APPLICATION ADVICE	Substrate Preparation: Before application of MC-CarboSolid 1209 TX all substrates must be verified for load-bearing capacity and prepared by means of a suitable surface blasting method. The substrates must be dry (residual moisture ≤ 6 %, CM-method), free of cement laitance, dust, oil and other contaminants. A minimum pull-off strength of 1.5 N/mm ² is required. The bonding surfaces of the substrate must be protected from increasing backwards moisture. Before application of CF-sheets the evenness of the concrete surface must be checked. The levelling mortar MC-CarboSolid 1000 can be used for levelling (roughness < 1.5 mm) according to the application advice indicated in the technical data sheet.
	Mixing and Application: MC-CarboSolid 1209 TX consists of two components, supplied in prepacked quantities. First, the base component is mixed thoroughly and then the hardener is added. Both components are mixed together thoroughly and homogeneously for at least 3 minutes. Slowly rotating mixers with paddle (max. 300 rpm) are suitable for mixing. Care should be taken to keep entrainment of air to a minimum while mixing. After mixing the resin must be refilled into a clean container and mixed again. MC-CarboSolid 1209 TX is applied at least 0.5 mm thick onto the substrate, using a trowel, a scraper or similar tool. Afterwards the CF-sheets are pressed into the fresh adhesive, using a laminating roller or similar tool, and then coated with MC-CarboSolid 1209, applied with a roller. Care must be taken during application that the carbon fibres are completely embedded in the adhesive.
	General Information: High temperatures shorten while low temperatures extend all indicated times and intervals. As a rule of thumb a change in temperature of 10 °C either halves or doubles the indicated pot life. Furthermore please note that higher temperatures reduce both the viscosity and the thixotropic properties of MC-CarboSolid 1209 TX. Varnish runs must be avoided. MC-CarboSolid 1209 TX should be stored inside at cool temperatures.

Safety Advice: Please take notice of the safety information and advice given on the packaging labels and safety data sheets.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density (mixture)	kg/dm³	1.33	
Mixing ratio	p.b.w.	3 : 1	base component : hardener component
Viscosity	mPa⋅s		
E-modulus	N/mm²	approx. 4,700	
Tensile strength (steel/steel)	N/mm²	14	Punch 20 mm Ø
Working time	minutes		
12 kg container		50	at 20 °C
Consumption	kg/m²/mm	1.33	
Application conditions ¹⁾	°C	≥ 8 ≤ 40	air and substrate temperatures
		≥ 15 ≤ 25	material temperature
	%	< 85	rel. humidity
	К	3	above dew point
Layer thickness	mm	10	
	All technical	values are laborato	ry results determined at $21^{\circ}C \pm 2^{\circ}C$ and 50% relative humidity.

1) At substrate temperatures > 30 °C the different layers of MC-CarbonFiber Sheets must be applied fresh in fresh

Equipment cleaning agent	MC-Reinigungsmittel U	
Delivery form	12 kg packs	
Colour	grey	
Storage	Can be stored in cool and dry conditions for at least 12 months in original unopened packs. Protect from frost.	
Packaging disposal	Make sure single-use containers are completely empty.	
GISCODE : RE90		

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2400022449]