

MC-DUR PowerCoat 200

Primer and sealer



PRODUCT PROPERTIES

- Primer and sealer for MC-DUR PowerCoat 240 and MC-DUR PowerCoat 280
- High mechanical, thermal and chemical resistance
- Solvent-free

AREAS OF APPLICATION

- Food industry
- Metal and chemical industry
- Washing and tank interior cleaning facilities
- REACH-rated exposure scenarios: Inhalation: periodically, Water contact: periodically, Processing

APPLICATION ADVICE

Substrate preparation: See instruction leaflet "Substrate and Substrate Preparation". For surfaces with hot loads (> 60 °C), reaction resin-bonded and bituminous layers are not permitted in the substrate.

Bonding grooves: To prevent the coating from cupping, bonding grooves (depth and width of the bonding grooves = at least twice the layer thickness) must be cut into the substrate close to the edge on all free edges of a day section and on all components penetrating the coating.

Mixing: MC-DUR PowerCoat 200 consists of four components, component A (base), component B (hardener), component C (aggregate) and MC-DUR PowerCoat Color component D (pigment), which are supplied in containers with matching quantities. Shake the containers of components A and B before use. First put component A into a clean mixing vessel and stir in component D MC-DUR PowerCoat Color (pigment). Then stir in component C. Stir the components with a slow-running stirrer for approx. 1 minute until a homogeneous, streak-free mixture is obtained. The hardener (component B) is now added to the premixed resin components and mixed homogeneously for a further 2 minutes.

Application as primer: After mixing, MC-PowerCoat 200 is rolled onto the substrate and sprinkled with oven-dried quartz sand 0.5 - 1.2 mm when fresh. The primer can be recoated after 12 hours at 20 °C at the earliest. The grooves are also primed. Make sure that no excess material of the primer fills the bonding grooves.

Application as a sealer: The unbound scattering grain is to be removed before applying the Remove the unbound scattering grain before applying the sealer. MC-DUR PowerCoat 200 is poured onto the substrate after mixing and then immediately spread evenly with a hard rubber float or rubber squeegee. Then roll on fresh in fresh with a short-pile lambskin roller.

Important notes: The optimum temperature of the components during mixing and processing is between 15 and 25 °C. In addition to the material temperature, the temperature of the substrate is important when working with PU/mineral hybrid floors. At low temperatures, the chemical reactions are delayed; this also extends the recoating and walkability times. At the same time, the viscosity increases. At high temperatures, the chemical reactions are accelerated, so that the times listed in the table are shortened accordingly. The resulting surface structure is strongly dependent on the construction site conditions as well as the processing. Due to the short reaction time, the coating measures must be well planned and prepared. Consumption quantities, application time, walkability and achievement of load-bearing capacity depend on the temperature and project conditions. Please refer to the information sheet "Processing of Reactive Resins". Please observe the further notes in the section "Processing of Reactive Resins" with regard to batch colour consistency. PU/mineral hybrid floors are functional floor coatings and are not colour-stable. Chemical stress and exposure to light can lead to changes in colour shade, which generally do not affect the suitability for use. It is recommended to regularly check and maintain chemically and mechanically stressed surfaces.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Mixing ratio	mass fractions	2.5 : 2.6 : 2.55 : 0.15	base component : Hardener component : aggregate : pigment
Density	g/cm ³	1.38	
Working time	minutes	15	at 20° C and 50 % rel. humidity
Accessible after	hours	approx. 8	at 20° C and 50 % rel. humidity
Resilient after	hours	approx. 24	at 20° C and 50 % rel. humidity
Resilient after (mechanically full)	hour	approx. 48	at 20° C and 50 % rel. humidity
Application conditions ¹⁾	°C	> 10 < 30	air and substrate temperatures
	%	< 85	rel. humidity
	K	3	above dew point
Consumption	kg/m ²		
Primer		0.4	
Top seal coat		0.6 - 0.8	depending on strewing material and grain size

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

1) Viscosity and consumption depending on material temperature.

Equipment cleaning agent	MC-Verdünnung PU
Colour	light grey, red, green, yellow
Delivery form	Component A: 2.5 kg canister Component B: 2.6 kg canister Component C: 2,55 kg bucket MC-DUR PowerCoat Color: 150 g bag (20 pieces per box)
Storage	Can be stored in cool (below 20°C) and dry conditions for 12 months in original unopened packs. Protect from frost. Component C can be stored for 9 months.
Packaging disposal	Make sure single-use containers are completely empty.
EU Regulation 2004/42 (Decopaint Directive)	RL2004/42/EG All/j (500 g/l) < 500 g/l VOC

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : PU40

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300019416]