

MC-Estribond T 15

Primer for cement based substrates

Product Properties

- Liquid
- Single-component
- Solvent free
- Reduces absorbency
- Stabilizing effect
- Can be sprayed and rolled

Areas of Application

- Primer for absorbent substrates underneath MC-Estrifan SN 10 and MC-Estrifan SN 25
- Primer for absorbent substrates underneath Concrete Cosmetics
- Slight stabilization of dusting and sanding substrates
- Deep primer for highly absorbent substrates

Application Notes

Substrate Preparation

The substrate must be clean, dry, load-bearing and free of all loose particles, dust, oil and other separating substances. Existing coatings must be removed. When used as primer underneath MC-Estrifan SN 10 and MC-Estrifan SN 25, it is recommended to thoroughly pre-wet mineral substrates. Puddle-formation should be avoided.

Application

MC-Estribond T 15 is ready to use and is applied undiluted with brush or roller. Apply only small amounts to avoid the formation of a shiny, adhesion-reducing surface-film. Puddle-formation should be avoided under any circumstances. Highly absorbent substrates should be primed twice. Depending on the absorbency and rough-ness of

the substrate, approx. 150 - 250 ml/m² of MC-Estribond T 15 is required. Deviations from this average can be determined in object-related preliminary tests.

MC-Estrifan SN 10 or MC-Estrifan SN 25 can be applied as soon as the primer is completely dry. Longer waiting periods before the application of the subsequent coatings can lead to adhesion-reducing contaminations and should therefore be avoided.

Further Information

Consumption, processing time and all technical properties depend very much on the temperatures and the object conditions.



Technical Data for MC-Estribond T 15

Characteristic	Unit	Value	Comments
Colour		white-milky	
Basis			plastic dispersion
Density	g/cm ³	approx. 1.02	
Consumption	ml/m ²	approx. 150 - 250	depending on the substrate
Can be overworked after	hours	approx. 1	at 20 °C and 50 % relative humidity

Product characteristics for MC-Estribond T 15

Internal Quality Control	DIN EN ISO 9001
Consistency	liquid
Form of Delivery	10 l canister
Storage	Can be stored for at least 12 months. Keep frost-free!
Disposal	For the sake of our environment please empty the packs completely!

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 04/17. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.