

PRODUCT PROPERTIES

- Cement-based, ready to use - just mix with water
- Fast setting, approx. 60-120 seconds after water is added
- Fast and permanent water infiltrations close off
- Swellable and shrink compensated
- Chloride free
- Certified acc. to EN 1504-3, class R1

AREAS OF APPLICATION

- Fast and permanent close off of leaks and water infiltration in concrete, masonry and natural stone constructions
- Sealing of cable and pipe inlets
- Sealing of damaged pipe sockets and manhole ring joints
- Creation of grooves under water pressure
- Sealing of slotted walls

APPLICATION ADVICE

Substrate Preparation: The substrate must be clean, solid and free from anti-adhesive substances as dust, oil, fat, cement lime, etc. The substrate should be pre-wetted. Dry substrates have to be pre-wetted intensively.

No movements should appear when sealing cracks or joints. To avoid adhesion problems in case of water infiltration, the leaks must be levered up for minimum 2 cm deepness.

Mixing: MC-Fast SM has to be mixed 15 - 20 seconds until a stiff-plastic mortar is obtained. Because of the fast processing time, it is recommended to mix a small amount of the material only.

MC-Fast SM has approx. 1 - 2 minutes workability time at + 23 °C, after water addition.

Processing: In case of water infiltrations the set mortar has to be pressed deep into the indentation by hand (protective gloves are recommended) for 1 - 2 minutes.

Immediately after this, any excess material can usually be removed with a trowel or similar. When doing this, always work with outwards from the middle, other wise there is a risk of the not get fully cured mortar becoming detached from the substrate.

In cold conditions the setting time can be accelerated by heating the water (lukewarm). In warm conditions the setting time can be extended by cooling the water.

Note: MC-Fast SM is a rigid sealing product. Due to subsequently appearing cracks in the construction work settings and deformations may lead into further leaks.

To avoid humidity loss in the surrounding of the application area, it must be sealed with sealing slurry MC-Proof 101 HS.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Fresh mortar bulk density	kg/dm ³	approx. 1.6	
Mixing ratio		5 : 1	base component : water
Mixing time	seconds	> 15 < 20	
Working time	minutes	1 - 2	
Application conditions	°C	≥ 5 ≤ 30	air, substrate and material temperatures
Consumption (flat)	kg/m ²		depending on condition of substrate
Dry mortar		approx. 1.7	per mm layer thickness
Flexural strength	N/mm ²		
1 h		3	
3 h		3.5	
4 h		4	
24 h		5	
7 d		5	
28 d		5	
Compressive strength	N/mm ²		
1 h		8	
3 h		10	
		13	
24 h		25	
7 d		40	
28 d		40	

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Equipment cleaning agent	water
Colour	grey
Storage	Can be stored in original sealed packages at temperatures between 5°C and 25°C in dry conditions for at least 12 months.
Packaging disposal	Make sure single-use containers are completely empty.

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : ZP1

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2400021874]