

MC-Fastpack EP solid

Highly reactive universal adhesive for rigid glueing and coating



PRODUCT PROPERTIES

- Ready-to-use 2-component epoxy-based adhesive
- Thixotropic, stable, fillable
- Adheres well to dry and moist mineral, metallic and ceramic surfaces
- Rapid strength development
- High compressive and tensile strength
- Applicable at low temperatures
- Comfortable hand processing from double-chamber cartridges
- High chemical resistance to acids and alkalis
- REACH exposure: water contact permanent, inhalation periodic, processing and application
- Environmental Product Declaration EPD

AREAS OF APPLICATION

- Glueing concrete and steel (e.g. anchors, mounting parts)
- Glueing adhesive packers (e.g. MC-Surfacepacker LP), damming cracks for injection work
- Closing of wide cracks and kerfs
- Closing / leveling of drill holes, pores and cavities (epoxy resin filler)
- Small-scale coating repairs
- Permanently tight connection of pipe liners to sewer manholes
- Manual application with the MC-Fastpack Power-Tool

APPLICATION ADVICE

Preparatory measures: Prior to injection, the structure must be examined according to the state of the art and the rules of technology, and an injection concept must be planned.

Mixing the components: Components A and B of MC-Fastpack EP solid are mixed as they pass through the static mixer of the cartridge system as application proceeds and can be injected directly.

The working time of the resin depends on the ambient temperature. Cooling the cartridges can extend the working time. Heating shortens the working time.

Application: Two-component injection is implemented with the MC-Fastpack Power-Tool (interchangeable cartridge tray 1:1/2:1). Depending on the application, MC-Fastpack EP solid can be processed with spatulas or smoothers or can be injected.

The adhesive must be carefully worked into the adhesive surface after application. In boreholes or anchor openings, cavities must be filled from the back to the front. The mixing tip can be extended for filling deep holes.

The processing time of the MC-Fastpack EP solid is influenced by the temperature of the adhesive, the temperature of the substrate and the layer thickness of the adhesive. If the work is interrupted longer than the processing time allows, the static mixer must be replaced with a new one. Opened cartridges must be closed with the original cap and can be used again promptly (≥ 7 days).

Special notes: Chemical exposure and exposure to light can lead to changes in color that do not affect usability.

Application work should cease once component/substrate temperatures fall below 5 °C.

Ensure compliance with the information given in the specifications and the Safety Data Sheets.

Equipment cleaning: The cartridge system means that the equipment is unlikely to need cleaning. If soiling does occur, all solvent-resistant tools can be cleaned with MC-Cleaner eco or thinner product MC-Verdünnung EP. Material that has reacted or set will need to be removed mechanically.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Mixing ratio	parts by volume	2 : 1	comp. A : comp. B
Working time	minutes	approx. 7	temperature-dependent
Consistency		pasty	stable up to approx. 10-15 mm
Substrate moisture content			mineral surface without pore water dry to matt damp
E-modulus	N/mm ²	approx. 5,800	EN ISO 178
Tensile strength (concrete)	N/mm ²		EN ISO 1542
		≥ 2.5	100% fracture in the concrete
Tensile strength (steel, blasted)	N/mm ²		EN ISO 4624
4 h		approx. 10	
8 h		approx. 15	
24 h		approx. 20	
Compressive strength	N/mm ²	approx. 85	EN ISO 604
Application conditions	°C	2 - 40	component and subsoil temperature
Density	kg/dm ³		EN ISO 2811-1
		approx. 1.5	
Viscosity	Pa · s		EN ISO 3219
		approx. 80	mix
		approx. 100	component A
		approx. 35	component B

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

equipment cleaning agent	MC-Verdünnung EP (thinner), under no circumstances should water or aqueous cleaning agents be used
delivery form	400 ml double-chamber cartridge with a volume ratio of 2 : 1 8 cartridges with 10 static mixers per box.
colour shade	grey
Storage	Can be stored in original sealed packages at temperatures between 10°C and 25°C in dry conditions for at least 24 months.
packaging disposal	Make sure single-use containers are completely empty. Ensure compliance with our information leaflet "Return of Emptied Transportation and Sale Packaging". We will be glad to send you this on request.

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GHS CODE : RE30

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2100005054]