

MC-PowerFlow 2237-3

high performance superplasticizer based on the MC-Polymer-Technology



PRODUCT PROPERTIES

- Good water-saving
- Economic dosage
- Long slump retention
- Fast mixing in concrete
- Low adhesiveness
- Good stabilisation at high consistencies
- Good compatibility with air-entraining agent
- Free of corrosion promoting components

AREAS OF APPLICATION

- Ready mixed concrete
- For combinations with composite-cement
- Concrete with high flowability
- Self-compacting concrete (SCC)

APPLICATION ADVICE

MC-PowerFlow 2237-3 is a synthetic superplasticizer based on the MC-Polycarboxylatether-technology.

The specific functioning-mechanism makes it possible to produce concrete with extremely low water contents and excellent workability. The desired properties of the fresh concrete can be achieved with moderate dosages.

The special combination of the active agent permits the production of homogeneous concrete of all consistency classes.

MC-PowerFlow 2237-3 requires relatively short mixing times to develop its full plasticizing effect. Therefore, a fast and economic concrete production is possible.

MC-PowerFlow 2237-3 has been developed to provide long slump retention. The frequently occurring slump losses with conventional plasticizing admixtures can be reduced considerably in many cases. An additional dosage of the superplasticizer, for a subsequent correction of the consistency on site is therefore in most cases no longer necessary.

Many former plasticizing admixtures with long slump retention showed extremely negative retarding side effects. With MC-PowerFlow 2237 normally good early strength development is achieved. However, in some exceptional cases and depending on the dosage and the temperatures, slight retarding side effects may occur.

MC-PowerFlow 2237-3 is added to the concrete during mixing. It is most effective when added after the additional water. It is also possible to apply it with the added water. The mixing time should be long enough to allow the admixture to unfold its plasticizing effect completely. If a dosage on the construction site into the concrete trucks is necessary, please follow the corresponding rules.

MC-PowerFlow 2237-3 can be used in combination with other MC admixtures. In individual cases please ask for our advisory service for concrete-technology.

Please note the "General Information on the Use of Concrete Admixtures".

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm ³	approx. 1.03	± 0.02 kg/dm ³
Recommended dosage range	g	2 - 50	per kg cement
Chloride content (maximum)	%	< 0.1	mass fraction
Alkaline content (maximum)	%	< 1.0	mass fraction
Self-monitoring	EN ISO 9001		
Type of admixture	High range water reducing admixtures/superplasticizing admixture for concrete - EN 934-2:T3.1/3.2 , Water reducing/plasticizing admixture for concrete - EN 934-2:T2		
Designation of admixture	MC-PowerFlow 2237-3		
Colour	brown		
Form	liquid		
Notified body	Karlsruher Institut für Technologie (KIT) Materialprüfungs- & Forschungsanstalt, MPA Karlsruhe, Notified Body number: 0754		
In-company production control	EN ISO 9001, EN 934-2/6		
Colour code of label	yellow/grey		
Delivery form	200 kg drums, 1000 kg container		

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300019883]