

MC-PowerFlow 3100

high-performance superplasticizer based on the newest MC-Polymer-Technology



PRODUCT PROPERTIES

- Short mixing-time
- Rapid effect
- Minimal adhesiveness
- Above average water-saving
- Economic dosage
- High initial strength
- High-quality concrete surfaces
- Free of corrosion promoting components
- Reduced setting time

AREAS OF APPLICATION

- Pre-cast elements
- Concrete with high flowability
- Self-compacting concrete (SCC)
- High-performance concrete
- High- strength concrete
- Fair-faced concrete
- Concrete with high resistance against aggressive agents
- Ready mixed concrete

APPLICATION ADVICE

MC-PowerFlow 3100 is a superplasticizer based on the newest MC-Polycarboxylatether-technology. A strong plastification results from a high adsorption rate.

Therefore MC-PowerFlow 3100 is especially appropriate to use in factories for pre-cast elements with a high degree of reinforcement and in producing prestressed concrete.

MC-PowerFlow 3100 is added to the concrete during mixing. It is most effective when added after the addition water. It is also possible to dose it with the added water.

The specific functioning-mechanism allows to produce concrete with extremely low water contents and high-performance concrete with excellent processing properties at economic dosages. The mixing-time is reduced noticeable.

With an unchanged water content the consistency can be increased by several consistency classes.

MC-PowerFlow 3100 makes it possible to produce high-tech concrete without increasing the adhesiveness. So the placing is easier and faster.

The special combination of the active agent permits to produce homogenous concrete without segregation. Thereby MC-PowerFlow 3100 can achieve high quality fair-faced concrete.

MC-PowerFlow 3100 can be used in combination with other MC admixtures. In individual cases please contact our concrete technology department for advice.

Please note the "General Information on the Use of Concrete Admixtures".

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm ³	approx. 1.06	± 0.02 kg/dm ³
Recommended dosage range	g	1 - 50	per kg cement
Chloride content (maximum)	%	< 0.1	mass fraction
Alkaline content (maximum)	%	< 2.0	mass fraction

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Self-monitoring	EN ISO 9001
Type of admixture	plasticiser per EN 934-2: T3.1/3.2, Concrete plasticisers EN 934-2: T2
Designation of admixture	MC-PowerFlow 3100
Colour shade	brown
Form	liquid
Notified body	MPA Karlsruhe
In-company production control	DIN EN ISO 9001 / DIN EN 934-2/6
Certificate of conformity of in-company production control	0754-CPR
Colour code of label	yellow/grey
Delivery form	30 kg canister, 200 kg barrel, 1000 kg IBC

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2200008080]