

# MC-PowerFlow 3102

high performance superplasticizer based on the MC-Polymer-Technology



## PRODUCT PROPERTIES

- Above average water-saving
- Rapid effect
- Short mixing-time
- Minimal adhesiveness
- High initial strength
- High-quality concrete surfaces
- Economic dosage
- Free of corrosion promoting components

## AREAS OF APPLICATION

- Pre-cast elements
- High-performance concrete
- Concrete with high flowability
- High-strength concrete
- Self-compacting concrete (SCC)
- Ready-mixed concrete
- Concrete with high resistance against aggressive agents
- Fair-faced concrete

## APPLICATION ADVICE

MC-PowerFlow 3102 is a superplasticizer based on the MC-Polycarboxylatether-technology. A strong plastification results from a high adsorption rate.

A special reaction mechanism enhances the development of high initial strength. Therefore MC-Powerflow 3102 is particularly suitable for the pre-cast concrete production. It is possible to achieve high quality fair-faced concrete.

MC-Powerflow 3102 provides concrete with reduced stickiness, improving the workability and placing. Therefore it is possible to achieve economic dosages. The mixing time is reduced and the dosage can be realized before or after adding water.

The usage of MC-Powerflow 3102 enables over the whole consistency range a stable, not segregating concrete. By not changing the water content the possibility of expansion of the consistence over several levels is given.

MC-PowerFlow 3102 can be used in combination with other MC admixtures. In individual cases please contact our concrete technology department for advice.

Using it in ready-mixed concrete it is important in case of construction dosage in vehicle to have a look at the rules.

Please note the "General Information on the Use of Concrete Admixtures".

## TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm <sup>3</sup>	approx. 1.06 ± 0.02	kg/dm <sup>3</sup>
Recommended dosage range	g	2 - 50	per kg cement
Chloride content (maximum)	%	< 0.1	mass fraction
Alkaline content (maximum)	%	< 1.5	mass fraction

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Self-monitoring	EN ISO 9001
Type of admixture	plasticiser per EN 934-2: T3.1/3.2
Designation of admixture	MC-PowerFlow 3102
Colour shade	brown
Form	liquid
Notified body	MPA Karlsruhe
In-company production control	EN 934-2/6
Certificate of conformity of in-company production control	0754-CPR
Colour code of label	yellow/grey
Delivery form	30 kg canister, 200 kg barrel, 1000 kg IBC

### Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

**Note:** The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2200006230]