

MC-PowerFlow 5105

High performance superplasticizer for the ready-mix concrete industry Based on the newest MC-Polymer-Technology



PRODUCT PROPERTIES

- Fast mixing in concrete
- Long slump retention
- Good compatibility with air-entraining admixture
- Low adhesiveness
- Good water-saving
- Economic dosage
- Good stabilisation at high consistencies
- Free of corrosion promoting components

AREAS OF APPLICATION

- Ready mixed concrete
- Concrete with high fluidity
- For combinations with composite-cement
- Self-compacting concrete (SCC)

APPLICATION ADVICE

MC-PowerFlow 5105 is a synthetic superplasticizer based on the newest MC-Polycarboxylatether-technology.

An additional dosage of the superplasticizer, for a subsequent correction of the consistency on site is therefore in most cases no longer necessary. In some exceptional cases and depending on the dosage and the temperatures slight retarding side effects may occur.

MC-PowerFlow 5105 is added to the concrete during mixing. It is most effective when added after the addition water. It is also possible to dose it with the added water. The mixing time should be long enough to allow the admixture to unfold its plasticizing effect during mixing.

MC-PowerFlow 5105 has been developed to provide long slump retention. The frequently occurring slump losses with conventional plasticizing admix- tures can be reduced considerably in many cases.

MC-PowerFlow 5105 requires relatively short mixing times to develop its full plasticizing effect. Therefore, a fast and economic concrete production is possible.

The specific functioning-mechanism makes it possible to produce concrete with extremely low water contents and excellent workability. The desired properties of the fresh concrete can be achieved with moderate dosages.

In case of dosage on building site in vehicles of ready-mixed concrete, please follow the corresponding set of rules.

Please note the "General Information on the Use of Concrete Admixtures".

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm ³	approx. 1.04	
Recommended dosage range	g	2 - 50	per kg cement
Chloride content (maximum)	%	< 0.1	mass fraction
Alkaline content (maximum)	%	< 2.0	mass fraction

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Self-monitoring	EN ISO 9001
Type of admixture	plasticiser per EN 934-2: T3.1/3.2, Concrete plasticisers EN 934-2: T2
Designation of admixture	MC-PowerFlow 5105
Colour shade	brownish
Form	liquid
Notified body	Karlsruher Institut für Technologie (KIT) Materialprüfungs- & Forschungsanstalt, MPA Karlsruhe, Notified Body number: 0754
In-company production control	DIN EN ISO 9001 / DIN EN 934-2/6
Colour code of label	yellow/grey
Delivery form	200 kg drums 1,000 kg container

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300013723]