

Muraplast FK 22

Plasticiser



PRODUCT PROPERTIES

- Free of corrosion promoting components
- Intensive dispersion of the cement paste
- Good homogeneity of the concrete due to the chemical-physical effect
- Decreases the internal frictional forces within the concrete
- Strong plastification, thereby decreasing the amount of water required
- Application, spreading and compaction of concrete is made easier
- Cost effective dosage

AREAS OF APPLICATION

- Ready mixed concrete
- Steel fibre concrete
- Industrial flooring

APPLICATION ADVICE

Muraplast FK 22 is a strong plasticizing admixture for concrete in the consistency categories F2 to F6. Strong plastification can be achieved with low dosages.

Muraplast FK 22 can be used in combination with all standard cement types.

Muraplast FK 22 can be added on site. The original consistency can be F2, F3, or F4, if this consistency category has been attained by adding a plasticizing concrete admixture.

Due to its intense dispersing effect, Muraplast FK 22 causes strong plastification of the concrete, even if the amounts added are small. The aggregation of cement particles is reduced. The cement is better wetted and finely broken up. This creates easily workable concrete which requires little compaction.

Muraplast FK 22 strongly reduces the water requirement. By lowering the w/c-value initial and final strengths are increased considerably. Without increasing water content, it is possible to enhance the consistency by several consistency classes, e.g. from F2 to F6.

Muraplast FK 22 can be used in combination with other MC products in concrete.

Muraplast FK 22 is added to the concrete during mixing. It is most effective when added after the additional water. It is also possible to apply it with the added water. The mixing time should be long enough to allow the admixture to unfold its plasticizing effect during mixing. Please refer to the relevant regulations, especially if the admixture is added into the supply truck on the construction site.

Please note the "General Information on the Use of Concrete Admixtures".

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Density	kg/dm ³	approx. 1.13	± 0.03 kg/dm ³
Recommended dosage range	g	2 - 40	per kg cement
Chloride content (maximum)	%	< 0.1	mass fraction
Alkaline content (maximum)	%	< 3.5	mass fraction

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

Type of admixture	plasticiser per EN 934-2: T3.1/3.2, Concrete plasticisers EN 934-2: T 2		
Designation of admixture	Muraplast FK 22		
colour shade	brown		
form	liquid		
Notified body	MPA, Karlsruhe		
In-company production control	DIN EN ISO 9001 / DIN EN 934-2/6		
Certificate of conformity of in-company production control	0754-CPR		
Colour code of label	grey/yellow		
delivery form	200 kg drums 1,000 kg container Tank truck		

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : BZM10

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2100004603]