

Oxal WPw WTA

Finishing coat (restoration render WTA) in the Oxal restoration render system
hand- and machine-applied render



TECHNICAL VALUES & PRODUCT CHARACTERISTICS

Characteristic	Unit	Value	Comments
Maximum grain size	mm	1	
Mixing ratio	kg/l	25 : 5.6	powder component : water
Air void content of the fresh mortar	%	≥ 25	
Working time	minutes	approx. 30	at 20° C
Application conditions	°C	≥ 5 ≤ 30	air, substrate and material temperatures
Consumption	kg/m ² /mm	approx. 1.1	
Layer thickness	mm		
On pore-filling render		20	minimum total layer thickness
On preparatory render		15	minimum total layer thickness
		30	maximum total layer thickness
Overworkable after	day(s)/mm	1	top plaster coat / fine plaster coat
Total porosity (solid mortar)	Vol.-%	≥ 40	
Colour		natural white	
Delivery form		25 kg bag	
Storage		Can be stored in cool and dry conditions for at least 12 months in original unopened packs.	
Packaging disposal		Make sure single-use containers are completely empty.	



Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300018339]