

ombran MHP 15

Fast setting, highly sulphate-resistant mortar for coating and re-profiling structures in sewerage systems



PRODUCT PROPERTIES

- Cement-bounded, polymer-modified, one-component, C₃A-free binding agent
- Impermeable to water, resistant to freeze and de-icing salt attacks
- Can withstand heavy mechanical loads, fibre-reinforced, highly abrasion resistant
- Resistant to very severe sulphate attack
- Early resistance to water impact
- Suitable as coating system in public sewerage systems, durable down to pH \geq 3.5: resistant to impacts concrete is exposed to in exposition class XA3 according to EN 206
- WW-coating mortar (B1-XWW3) acc. to DIN 19573
- WW-jointing mortar (XWW3) acc. to DIN 19573
- WW-repair mortar (B2-XWW3, no exposure to weathering) acc. to DIN 19573
- Class R3 according to EN 1504-3 (structural relevant)
- General building supervision approval

AREAS OF APPLICATION

- Coating of concrete and masonry manholes, sewers as well as reservoirs
- Re-profiling of breakouts and defects in manholes, sewers and reservoirs
- Re-profiling and coating of channel area of wastewater structures
- Jointing of masonry and tiles / panels in wastewater structures
- Forming of fillets
- REACH-assessed exposure scenarios: periodical inhalation, application, long-term water contact

APPLICATION ADVICE

Substrate Preparation: See the data sheet "General Application Advice for manhole and sewer repair mortars".

Pre-wetting / Bonding Agent: See the data sheet "General Application Advice for manhole and sewer repair mortars". ombran HB must be used as the bonding agent, the details of the technical data sheet of ombran HB must be observed.

Mixing: The mineral re-profiling / coating consists of dry mortar ombran MHP 15 and water. Pour out the major part of the water, scatter the ready-mix mortar on it and mix to a uniform, lump-free consistency. The remaining water is used to adjust the consistency as necessary. Pug mill mixers and slow-running double stirrers are suitable for mixing the mortar. Mixing by hand and mixing of partial quantities is not allowed. Mixing takes at least 3 minutes.

Mixing Ratio: About 3.2 to 3.5 litres of water are needed for a 25 kg bag of ombran MHP 15. Since ombran MHP 15 is cement-bound, the amount of water needed may vary.

Application: ombran MHP 15 must be applied "fresh-in-fresh" onto the bonding agent using suitable tools (e.g. steel smoothing tool, trowel), compacted and abraded. Where a thick coating is required it may be necessary to apply multiple layers. If afterwards an additional protection material will be applied, roughen the surface of top mortar layer with suitable means (e.g. structuring with a coconut broom or sweeping).

Curing: During post-treatment, ombran MHP 15 must be protected from excessive water loss for at least 72 h (chemical curing agents e.g. MC-RIM PROTECT C, jute sacking, foil etc.). Particular attention must be given to the relevant effects of temperature and wind. If further layers of the material or subsequent coating systems are to be applied, the use of separating curing agents must be avoided or the surface must be intensively prepared by blasting to remove remaining curing layers.

TECHNICAL VALUES & PRODUCT CHARACTERISTICS

| Characteristic | Unit | Value | Comments |
|--|-----------------------|----------------|--|
| Mixing ratio | mass fractions | 25 : 3.2 - 3.5 | powder component : water |
| Working time | minutes | approx. 15 | at 20° C |
| Application conditions | °C | ≥ 5 ≤ 30 | air, substrate and material temperatures |
| Consumption (flat) ¹⁾ | kg/m ² /mm | 1.9 | factory-dried mortar |
| Layer thickness | mm | ≥ 6 | as a reprofiling mortar |
| | | ≥ 10 | per layer as coating mortar |
| | | ≤ 25 | per layer as coating mortar |
| | | 50 | maximum total layer thickness |
| Water resistant after | hours | approx. 1.5 | at 20° C |
| Maximum grain size | mm | approx. 2 | |
| Fresh mortar bulk density | kg/dm ³ | approx. 2.2 | |
| Compressive strength (strength development) | N/mm ² | | |
| | | 24 h | ≥ 8 |
| | | 7 d | ≥ 40 |
| | | 28 d | ≥ 43.5 |
| Flexural strength (strength development) | N/mm ² | | |
| | | 24 h | ≥ 3 |
| | | 7 d | ≥ 4.5 |
| | | 28 d | approx. 6 |
| E-modulus (static) | N/mm ² | approx. 18,100 | after 28 days |

All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.

1) object specific

| | |
|--------------------------|--|
| Equipment cleaning agent | water |
| Colour | grey |
| Delivery form | 25 kg bag |
| Storage | Can be stored in original sealed packages at temperatures between 5°C and 25°C in dry conditions for at least 12 months. |
| Packaging disposal | Make sure single-use containers are completely empty. |

Safety instructions

Please note the safety information and advice given on the packaging labels and safety data sheets. GISCODE : ZP1

Note: The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300018307]